

Jotashield Kanva

Product description

Type

This product is a high quality multicolour tintable waterborne texture paint. Based on a pure acrylic emulsion and contains coarse hard aggregates.



Features and benefits

A premium textured product - with just one coat, it provides a prominent grooved finish that is stunning and durable.

It is formulated with excellent weather resistance properties, ensuring that your walls stay protected from harsh climatic conditions. The long-lasting colors that do not fade and low dirt collection make your walls look beautiful and stay clean.

Available in a wide range of colors that can be tinted instantly, this allows you to customize the finish of your walls to suit your style.



Recommended use

Ideal for exterior and interior surfaces.

Substrate

Cement plaster, concrete, block work, rendered surfaces etc.

Conditions of use

Substrate should have sufficient strength to receive the paint. Any defects in the substrate like surface undulations, cracks, pin holes etc., should be rectified/filled before starting painting. The compatibility of any third party filling material, if used, shall be confirmed with Jotun before application.

Product data

Packaging size	16 L
Colours	This product is available with beautiful long lasting colours through instant in-store Multicolour tinting.
Solids by volume	60 ± 2 volume%
Specific gravity	1.88 Theoretical only for white colour.
VOC	23 g/l ISO 11890 EU
VOC comments	This is the theoretical value. Tested value will vary depending on test methodology, accuracy of equipment used for testing and test conditions.

Application data

The product can be applied by

Nylon or steel trowel and Putty knife

Film thickness per coat

Typical recommended range

Film thickness will vary and are calculated as an average.

Theoretical spreading rate 0.9 - 0.7 m²/l

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Thinner

Water

Dilution

The paint is ready to use after proper stirring. If thinning is required, water may be added up to a maximum of 5%.

Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. The ideal maximum substrate temperature during application should not be more than 45 °C. Good ventilation is usually required in confined areas to ensure proper drying.

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The drying time is measured by stated values:

Relative Humidity (RH) 50 %

Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	8 h	4 h	2 h
Hard dry	48 h	24 h	12 h
Dry to over coat, minimum	40 h	20 h	10 h

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Recommended paint system

Primer

Jotashield Alkali Resistant Primer or Jotashield Penetrating Primer : 1 Coat

Topcoat

Jotashield Kanva : 1 Coat

Remarks

Other systems may be specified, depending on area of use.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.